TECHNICAL DATA SHEET

Fiberglass mesh 160 g/m² – HITROM

TECHNICAL AGREEMENT - NR. 001SC-04/719-2018

DESCRIPTION

Fiberglass mesh (E-glass type), is a product characterized primarily by resistance to alkaline environment. It is coated with a layer of SBR (Styrene-Butadiene).

Using a LENO type fabric, the fiberglass mesh with the weight of 160 g/m² confers resistance to the wall rendering and a lifetime equal to that of the plasters it reinforce.

DESTNATION AND FIELD OF USE

- Fiberglass mesh with the weight of 160 g/m² is used as reinforcing element for external thermal insulation system (ETICS) based on mineral wool, expanded polystyrene or other type of thermal insulation board;
- Reinforcement of interior and exterior plasters, protecting them from cracking;
- Manufacture of reinforcement layers for facades renovations.

CHARACTERISTICS		TESTING METHOD	UNITS	TOLERANO	CE VALUES
Appearance of fiberglass scrim		SR EN ISO 7823-1:2003			without visible physical defects
Dimensions – material width		SR EN ISO 7823-1:2003	mm	±1%	1000
Dimensions – material length		SR EN ISO 7823-1:2003	mm	±1%	50000
Total weight per unit area		SR 137-95	g/m²	±5%	160
Tensile strength under normal storage conditions		SR EN 13496:2014	N/5 cm	±1%	1945
Tensile strength under normal storage conditions - CMD		SR EN 13496:2014	N/5 cm	±1%	2120
Elongation at break under no					
storage conditions - MD		SR EN 13496:2014	% min.		5
Elongation at break under normal					
storage conditions - CMD		SR EN 13496:2014	% min.		4
Tensile strength after 24 hours in alkaline solution at T = +60°C - MD		SR EN 13496:2014	N/5 cm		950
Tensile strength after 24 hours in alkaline solution at $T = +60$ °C		SR EN 13496:2014	N/5 cm		1115
SC BICO Industries SA610094 - Petru Movila nr. 31NRC: J27/1388/2006Piatra Neamţ, RomâniaCUI: RO 19241603730234 - Metalurgiei nr. 1Vaslui, România		+40 233 2 +40 233 2		officevs@bicoindustries.ro +40 235 311 079 T +40 235 311 079 F www.bicoindustries.ro	

TECHNICAL CHARACTERISTICS



- CMD Fire reaction class

F (without determined performance)

*MD = Machine Direction; CMD = Cross Machine Direction;

CERTIFICATIONS

The manufacturer S.C. BICO INDUSTRIES S.A. has implemented an integrated management system: quality, environment, occupational health and safety, according to ISO 9001, ISO 14001 and SR OHSAS 18001 - AEROQ certificates.

CLASSIFICATION ACCORDING TO CHEMICAL STANDARDS. POSSIBLE RISKS, PREVENTION REQUIREMENTS

Fiberglass mesh does not require marking and is not a dangerous product. According to Regulation (EC) no. 1907/2006 of the European Parliament and of the Council, fiberglass reinforcement does not require the safety data sheet.

SPECIFIC CONDITIONS, STORAGE, TRANSPORTATION

- Specific conditions: it is recommended to be stored in clean, dry places, at temperatures between -5°C and 30°C, protected from the direct radiation of any heat source or from the direct action of the sun's rays;
- **Storage:** to be stored in rolls positioned vertically, in covered and appropriate storages;
- Transportation: the rolls of fiberglass mesh, positioned vertically on pallets, are being transported with adequate and covered transportation.

Form code: F.PO-09.7.1/0

SC BICO Industries SA NRC: J27/1388/2006 CUI: RO 19241603 610094 - Petru Movila nr. 31 Piatra Neamţ, România office@bicoindustries.ro +40 233 211 400 T +40 233 211 500 F officevs@bicoindustries.ro +40 235 311 079 T +40 235 311 079 F

730234 - Metalurgiei nr. 1 Vaslui, România

www.bicoindustries.ro

www.bicoindustries.ro